Synthesis of silver orthophosphate under dimethyl sulfoxide solvent and their photocatalytic properties

| Publons ID | 36330773 |
|-----------------|--|
| Wos ID | WOS:000471058400151 |
| Doi | 10.1088/1757-899X/509/1/012151 |
| Title | Synthesis of silver orthophosphate under dimethyl sulfoxide solvent and their photocatalytic properties |
| First Author | Septiarini, Dyah Ayu; Kurniasih, Mardiyah; Andreas, Roy; |
| Last Author | Sulaeman, Uyi |
| Authors | Septiarini, DA; Kurniasih, M; Andreas, R; Hermawan, D; Sulaeman, U; |
| Publish Date | 2019 |
| Journal Name | 13TH JOINT CONFERENCE ON CHEMISTRY (13TH JCC) |
| Citation | 3 |
| Abstract | The silver orthophosphate was successfully synthesized using the starting materials of AgNO3, KH2PO4 under water and dimethyl sulfoxide (DMSO) solvents. The variation of DMSO in water was designed at 0, 5, 10, 15, 20 and 100% (v/v). The products were characterized by XRD, DRS, and SEM. The photocatalytic properties were evaluated under the blue light irradiation using the methyl orange degradation. The results showed that the DMSO significantly affected the morphology, particle size and bandgap energy of Ag3PO4. The addition of DMSO decreased the particle size of Ag3PO4 and changed the tetrahedron into an irregular shape. The bandgap energies of 2.33, 2.28 and 2.42 eV were observed in the sample prepared with the content of DMSO at 0, 15 and 100% respectively. The highest photocatalytic activity was found at 15% DMSO. This excellent photocatalytic activity might be due to the lower bandgap energy and the higher intensity ratio of [222]/[110] facet. |
| Publish Type | Book in series |
| Publish Year | 2019 |
| Page Begin | (not set) |
| Page End | (not set) |
| lssn | 1757-8981 |
| Eissn | |
| Url | https://www.webofscience.com/wos/woscc/full-record/WOS:000471058400151 |
| Author | ROY ANDREAS, S.Si, M.Si, Ph.D |